

### 布氏 - 洛氏 硬度换算表

布氏硬度	洛氏硬度			抗拉强度	布氏硬度	洛氏硬度			抗拉强度
碳化钨球 3000 Kg	A级 60 Kg	B级 100 Kg	C级 150 Kg	(约 psi)	碳化钨球 3000 Kg	A级 60 Kg	B级 100 Kg	C级 150 Kg	(约 psi)
-	85.6	-	68	-	331	68.1	-	35.5	166,000
-	85.3	-	67.5	-	321	67.5	-	34.3	160,000
-	85	-	67	-	311	66.9	-	33.1	155,000
767	84.7	-	66.4	-	302	66.3	-	32.1	150,000
757	84.4	-	65.9	-	293	65.7	-	30.9	145,000
745	84.1	-	65.3	-	285	65.3	-	29.9	141,000
733	83.8	-	64.7	-	277	64.5	-	28.8	137,000
722	83.4	-	64	-	269	64.1	-	27.6	133,000
712	-	-	-	-	262	63.6	-	26.6	129,000
710	83	-	63.3	-	255	63	-	25.4	126,000
698	82.6	-	62.5	-	248	62.5	-	24.2	122,000
684	82.2	-	61.8	-	241	61.8	100	22.8	118,000
682	82.2	-	61.7	-	235	61.4	99	21.7	115,000
670	81.8	-	61	-	229	60.8	98.2	20.5	111,000
656	81.3	-	60.1	-	223	-	97.3	20	-
653	81.2	-	60	-	217	-	96.4	18	105,000
647	81.1	-	59.7	-	212	-	95.5	17	102,000
638	80.8	-	59.2	329,000	207	-	94.6	16	100,000
630	80.6	-	58.8	324,000	201	-	93.8	15	98,000
627	80.5	-	58.7	323,000	197	-	92.8	-	95,000
601	79.8	-	57.3	309,000	192	-	91.9	-	93,000
578	79.1	-	56	297,000	187	-	90.7	-	90,000
555	78.4	-	54.7	285,000	183	-	90	-	89,000
534	77.8	-	53.5	274,000	179	-	89	-	87,000
514	76.9	-	52.1	263,000	174	-	87.8	-	85,000
495	76.3	-	51	253,000	170	-	86.8	-	83,000
477	75.6	-	49.6	243,000	167	-	86	-	81,000
461	74.9	-	48.5	235,000	163	-	85	-	79,000
444	74.2	-	47.1	225,000	156	-	82.9	-	76,000
429	73.4	-	45.7	217,000	149	-	80.8	-	73,000
415	72.8	-	44.5	210,000	143	-	78.7	-	71,000
401	72	-	43.1	202,000	137	-	76.4	-	67,000
388	71.4	-	41.8	195,000	131	-	74	-	65,000
375	70.6	-	40.4	188,000	126	-	72	-	63,000
363	70	-	39.1	182,000	121	-	69.8	-	60,000
352	69.3	-	37.9	176,000	116	-	67.6	-	58,000
341	68.7	-	36.6	170,000	111	-	65.7	-	56,000